



IBFeBeCu25

Is used for build-up, crack and repair welding in the mould and die industry Beryllium copper mainly used, where gliding properties, fast heat transmission and high conductance are required in combination.

Recommended for basic materials:

Beryllium copper

Rework:

Special information

Please note safety data sheet

Material analysis:

Be	Co	Ni	Fe	Si	Al	Cu
1,9	0,2	0,02	0,06	0,05	0,03	Rest

(test certificates upon request.)

Standard / Mechanical values:

Ø	N / mm ²	elongation AL100	Items on stock	
			rods	spools
0,2				
0,25				
0,3				
0,4				
0,5				
0,6				
0,7				
0,8				